

Product Specification

Reflective Series - Comparative Performance Data

	Reflective Blue 15	Reflective Bronze 15	Reflective Gold 15	Reflective Grey 15	Reflective Green 15
Visible Light Transmitted	8.8%	9.3%	14.6%	9.4%	14.6%
Glare Reduction	90.0%	89.4%	83.4%	89.3%	83.4%
Total Solar Energy Rejected	78.3%	76.5%	76.5%	75.6%	74.8%
Shading Coefficient	.25	.27	.27	.28	.29
Visible Light Reflected	24.7%	21.3%	38.9%	20.5%	31.7%
Ultra-Violet Rejection	Up to 99.0	Up to 99.0	Up to 99.0	Up to 99.0	Up to 99.0
Total Solar Energy Reflected	41.5%	32.0%	40.8%	31.2%	35.0%
Total Solar Energy Absorbed	48.9%	59.0%	47.8%	59.5%	52.9%
Total Solar Energy Transmitted	9.6%	9.0%	11.4%	9.3%	12.1%

Performance data is based on this film being applied to the inside of 1/4" clear monolithic annealed glass.